

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 284 148 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
19.02.2003 Bulletin 2003/08

(51) Int Cl.7: A61N 1/05

(21) Application number: 02015976.0

(22) Date of filing: 18.07.2002

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• Snichelotto, Eugenio
35121 Padova (IT)
• Baraldo, Marco
35121 Padova (IT)

(30) Priority: 06.08.2001 IT PD20010199


(74) Representative: Gustorf, Gerhard, Dipl.-Ing.
Patentanwalt,
Bachstrasse 6 A
84036 Landshut (DE)

(71) Applicant: Medico S.p.a.
35121 Padova (IT)

(54) Procedure for platinum coating of titanium cardiac electrodes

(57) The invention is a new procedure for platinum coating of titanium cardiac electrodes, comprising the spark erosion of the surface of the titanium electrode and the subsequent electrochemical deposition of platinum on the electrode. The spark erosion of the elec-

trode surface is performed in a solution of methanol and sodium chloride and, after the electrodeposition of platinum, the electrode is subjected to the action of a regulated flame in order to permanently fix the platinum to the titanium electrode.



Description

FIELD OF THE INVENTION

[0001] This patent concerns medical electrodes for intracardiac use and in particular it concerns a new procedure for platinum coating of titanium cardiac electrodes.

PRIOR ART

[0002] At present medical electrodes for intracardiac use are made of titanium and/or titanium with titanium nitride coating.

[0003] The electrodes produced in this way have the following problems and disadvantages.

[0004] The electrodes currently used remain partly polarised after stimulation, with the result that the stimulation signal is prolonged and distorted.

[0005] The electrodes currently used have a relatively high pacing threshold, which requires gauging of the pacing circuit in order to compensate for said threshold.

DESCRIPTION

[0006] To solve all the above problems, a new procedure for platinum coating of titanium cardiac electrodes has been studied and implemented.

[0007] The aim of the new procedure is to securely and uniformly fix the platinum coating on the titanium of the electrode.

[0008] Another purpose of the new procedure is to join platinum to the titanium of the electrode in a uniform manner, in order to eliminate any capacitive and resistance effect.

[0009] Procedure for platinum coating of titanium cardiac electrodes comprising initial spark erosion of the electrode surface, subsequent electrochemical deposition of platinum on the titanium surface which has been given a rough micro-finish, and final hot-fixing by means of regulated flame.

[0010] The characteristics of the new procedure for platinum coating of titanium cardiac electrodes will be clarified by the following description, with reference to the drawing attached as a non-restrictive example.

[0011] The titanium electrode (E) is produced in the necessary form and dimensions by means of the known procedures which are not discussed here.

[0012] The surface of the titanium electrode (E) is too smooth for the optimal deposition of platinum.

[0013] The electrode (E) is connected by an electric wire (F1) and the surfaces (P) not to be coated with platinum are protected.

[0014] The electrode (E) prepared as above is immersed in a solution of methanol and sodium chloride in which a titanium counter electrode (C) has been immersed, connected by a second electric wire (F2).

[0015] By applying electric current to the two wires

(F1, F2), spark erosion is performed on the exposed surface of the electrode (E), giving it a rough micro-finish. Said finish provides a better and safer surface for the adhesion of platinum.

5 [0016] Once spark erosion has been performed, the titanium electrode (E) is electrochemically coated with a layer of platinum. This second electrochemical phase deposits on the rough micro-finish surface of the electrode (E) a layer of platinum with thickness depending
10 on the duration of the electrochemical deposition process on the electrode (E).

[0017] Lastly, the electrode (E) coated with the layer of platinum is exposed to a regulated flame for permanent fixing of the platinum on the electrode.

15 [0018] The procedure for platinum coating of titanium cardiac electrodes described above produces cardiac electrodes with improved characteristics.

[0019] The rough micro-finish obtained on the surface of the electrode permits the improved adhesion of platinum on the electrode (E).


20 [0020] The hot-fixing of platinum on the electrode (E) permanently joins platinum to the surface of the electrode (E) and ensures uniformity in both the outer platinum surface and in the adhesion of platinum to the surface of the titanium electrode (E).


[0021] The electrode thus obtained consequently has a very low pacing threshold and is free from capacitive effects and post-stimulation polarisation.

30 [0022] With reference to the above description and the attached drawing, the following claims are therefore expressed.

Claims

- 35 1. Procedure for platinum coating of titanium cardiac electrodes, **characterised in that** it comprises the spark erosion of the surface of the titanium electrode (E) and the subsequent electrochemical deposition of platinum on the electrode (E).
- 40 2. Procedure for platinum coating of titanium cardiac electrodes according to claim 1, **characterised in that** the spark erosion of the electrode surface (E) is performed in a solution of methanol and sodium chloride.
- 45 3. Procedure for platinum coating of titanium cardiac electrodes according to claims 1 and 2, **characterised in that** the electrode (E), after the electrodeposition of platinum, is subjected to the action of a regulated flame in order to permanently fix the platinum to the titanium electrode.





Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 284 148 A3**

(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
10.12.2003 Bulletin 2003/50

(51) Int Cl.7: **A61N 1/05**

(43) Date of publication A2:
19.02.2003 Bulletin 2003/08

(21) Application number: **02015976.0**

(22) Date of filing: **18.07.2002**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Snichelotto, Eugenio**
35121 Padova (IT)
• **Baraldo, Marco**
35121 Padova (IT)

(30) Priority: **06.08.2001 IT PD20010199**


(74) Representative: **Gustorf, Gerhard, Dipl.-Ing.**
Patentanwalt,
Bachstrasse 6 A
84036 Landshut (DE)

(71) Applicant: **Medico S.p.a.**
35121 Padova (IT)

(54) **Procedure for platinum coating of titanium cardiac electrodes**

(57) The invention is a new procedure for platinum coating of titanium cardiac electrodes, comprising the spark erosion of the surface of the titanium electrode and the subsequent electrochemical deposition of platinum on the electrode. The spark erosion of the elec-

trode surface is performed in a solution of methanol and sodium chloride and, after the electrodeposition of platinum, the electrode is subjected to the action of a regulated flame in order to permanently fix the platinum to the titanium electrode.





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 01 5976

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	EP 0 839 553 A (HERAEUS GMBH W C) 6 May 1998 (1998-05-06) * column 1-3; claims 7,16,19 *	1-3	A61N1/05
Y	EP 0 596 589 A (TELECTRONICS NV) 11 May 1994 (1994-05-11) * column 3, line 45 - line 58 * * column 4, line 36 - column 5, line 6 * * column 13, line 3-6 *	1-3	
A	EP 0 043 461 A (SORIN BIOMEDICA SPA) 13 January 1982 (1982-01-13) * the whole document *	1-3	
A	US 5 181 526 A (YAMASAKI HARUKI) 26 January 1993 (1993-01-26) * the whole document *	1-3	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			A61N
Place of search		Date of completion of the search	Examiner
MUNICH		17 October 2003	BIRKENMAIER, T
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date O : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03.02 (P/MC01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 01 5976

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-10-2003

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0839553	A	06-05-1998	DE	19645155 A1	07-05-1998
			EP	0839553 A2	06-05-1998
EP 0596589	A	11-05-1994	US	5326448 A	05-07-1994
			DE	596589 T1	08-12-1994
			EP	0596589 A1	11-05-1994
EP 0043461	A	13-01-1982	IT	1128813 B	04-06-1986
			DE	3162361 D1	29-03-1984
			EP	0043461 A1	13-01-1982
US 5181526	A	26-01-1993	JP	4002366 A	07-01-1992
			JP	4002367 A	07-01-1992

EPO FORM P0469

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82